

Page 1 of 2

TECHNICAL DATA SHEET Vulkollan® D15, 90 +-5 Shore A, natural

Properties

Hardness Shore A DIN 53505 85 - 95 SHA Color natural Density 1 26 g/cm3 °C Temperature range -15 - +80 Tear resistance DIN 53504 MPa 40 Elongation at break DIN 53504 660 Tear propagation resistance DIN 53507 55 N/mm Abrasion loss DIN 53516 32 mm³ Oil resistance very good

Resistance to gasoline good
Resistance to acids limited
Alkali resistance limited

Comments IMDS data available Compression set 24h, $70 \,^{\circ}\text{C} = 20 \,^{\circ}\text{M}$

VULKOLLAN® is a registered trademark of Covestro Group

Hydrolysis resistance:

This material is manufactured with the addition of hydrolysis protection agents.

Hydrolysis is regarded as the time-related drop of typical technical parameters such as e.g. tensile strength, elongation at break and tear propagation resistance, which is initiated above all by water or moisture in combination with heat. The extent of the change is thereby dependent on the duration and intensity of the influence.

Vulkollan D15 is basically equipped so that an improved hydrolysis protection is provided in comparison to polyurethanes that are not especially protected. Nevertheless a drop in the technical characteristic values can be determined, however this change is slowed considerably. Overall however the resistance to the influences of hydrolysis is lower than for Vulkollan and standard polyurethane as produced by QUADRIGA.

An unambiguous statement about the hydrolysis resistance (as for instance with statements about the resistance to certain chemicals) is not possible, since the limit values vary greatly depending on the respective case of application.

Referenced standards correspond to the version number of the data sheet provided by our raw material supplier. All details are mean values. Our recommendations are given to the best of our knowledge. They are however without obligation, and we cannot accept any liability for damage or disadvantages of any kind, including in relation to third-party property rights.



QUADRIGA Dichtungs-GmbH

Gutenbergring 47

22848 NORDERSTEDT
GERMANY
T +49 40 528 704-0
F +49 40 523 73 24
info.quadriga@spaeh.de
www.guadriga-polyurethane.com

Issue: 06/04/16



Page 2 of 2

Resistances

	During the influence at room temperature	After short-term influence at room temperature
Acids and alkaline solutions:		
concentrated	destroyed	destroyed
diluted (< 3 %)	Volume swelling <20%, low loss in strength	original volume; original strength
Saturated hydrocarbons Crude oil, diesel fuel, gasoline	Volume swelling <20%, low loss in strength	original volume; original strength
Aromatic hydrocarbons: Super fuel, benzene, toluene, xylene	Volume swelling <20%, significant loss in strength	original volume; original strength
Lubricating oils and greases: ASTM-test oil 1, 2, 3, diesel fuel, Gasoline	Volume swelling <20%, low loss in strength	original volume; original strength
Alcohols: Methanol, ethanol	Volume swelling <20%, low loss in strength	original volume; original strength

In contrast to other plastics, Vulkollan D15 is resistant to ozone and UV-radiation. Evidence for this are the ship- and harbor bumpers. Even after many years exposed to weathering in the ocean climate, no drop in the usage properties was determined with this material.

The resistance to chemicals depends to a great extent on the duration of the contact, the predominant temperature as well as on the quantity and concentration of the respective chemical. Insofar only general information can be provided in the table.

For other chemicals not listed here or for deviating conditions of the contamination, if needed tests can be carried out. That also applies for the chemicals and fuels specified here, if these should come into contact with Vulkollan D15 not in pure form, rather mixed with additives.



QUADRIGA Dichtungs-GmbH

Gutenbergring 47 22848 NORDERSTEDT GERMANY T +49 40 528 704-0

T +49 40 528 704-0
F +49 40 523 73 24
info.quadriga@spaeh.de
www.guadriga-polyurethane.com

Referenced standards correspond to the version number of the data sheet provided by our raw material supplier. All details are mean values. Our recommendations are given to the best of our knowledge. They are however without obligation, and we cannot accept any liability for damage or disadvantages of any kind, including in relation to third-party property rights.

Issue: 06/04/16